



Catoxid[®] 5 Catalyst Specification

<i>Chemical Analysis</i> (550 °C dry weight basis)	<u>Min</u>	<u>Max</u>
Chromium, Wt. %	4.6	5.8
<i>Physical Properties</i> (550 °C dry weight basis)		
Loss on Ignition, Wt. %	----	3
Bulk Density, g/cc (packed)	0.8	1.0
<i>Particle Size Distribution</i>		
Laser Light Scattering Analysis		
% Less than 88 microns	70	100
% Less than 22 microns	----	10

Per the Non-disclosure Agreement on this Patented Proprietary Catalyst, executed between Oxy Vinyls, LP and your company, the information provided here is strictly confidential and is not to be disclosed to any third party, without the permission of Oxy Vinyls, LP.