



OxyVinyls[®] 226



General Description

Type: Polyvinyl Chloride Homopolymer
Polymerization Process: Suspension
Appearance: White, free flowing powder

Features and Uses:

Flexible Film and Sheet
Molding and Profile Extrusion Applications
Wire and Cable Insulation
Low Gels and Contamination
Uniform Plasticizer Absorption
Excellent Color and Clarity

Resin Properties	Typical Value	Specification Range	Test Method
Inherent Viscosity (dl/g)	0.950	0.930 – 0.970	OxyVinyls 1386
Relative Viscosity	2.24	2.20 – 2.28	Correlation
K Value	67	66 – 67	Correlation
Volatiles (%)	0.05	0.3 Max.	OxyVinyls 1242
Malvern Particle Size			
% Retained on 40 mesh	0.0	0.2 Max.	OxyVinyls 1505
% Retained on 60 mesh	2.0	4.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	12.0	15.0 Max.	
% Retained on Pan	2.0	5.0 Max.	
Contamination (#/100gm)	9	15 Max.	OxyVinyls 1504
Residual Monomer (ppm)	0.03	2.0 Max.	OxyVinyls 1005
Porosity (cc/g)	0.339	0.300 – 0.390	OxyVinyls 1094
Apparent Bulk Density (g/cc)	0.520	0.480 – 0.570	OxyVinyls 1501
Flow Time (s)	9	12 Max.	OxyVinyls 1501
Powder Mix Time (s)	296	250 – 350	OxyVinyls 488
Color (CIELab b*-value)	0.60	0.30 – 1.30	OxyVinyls 1500
Gels (4' mill results)	10	20 Max.	OxyVinyls 1503
CAS Number	9002-86-2		

OxyVinyls, LP
Occidental Tower
5005 LBJ Freeway
Dallas, Texas 75244
877-699-8465

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.