



SALES SPECIFICATION

Calcium Chloride Pellets 90

<u>Property</u>	<u>Minimum</u>	<u>Maximum</u>
Calcium Chloride (wt. %)	90.0	
Total Alkali Chlorides as NaCl (wt. %)		6.0
Total Magnesium as MgCl ₂ (wt. %)		0.5
Calcium Hydroxide (wt. %)		0.2
Passing 3/8 in. (9.5 mm) sieve (wt. %)	100	
Passing No. 4 (4.76 mm) sieve (wt. %)	80	
Passing No. 20 (0.84 mm) sieve (wt. %)		10
Passing No. 30 (0.6 mm) sieve (wt. %)		1
Bulk Density, Tapped (lb/ft ³)	58	66

Material description: white, odorless pellets

Total Alkali Chlorides as NaCl (wt %), Total Magnesium as MgCl₂ (wt %) and Calcium Hydroxide (wt %) limits are shown on an "Active Ingredient" basis.

Meets ASTM D98 and AASHTO M144 requirements.

SS-P9B Sep 2018



Occidental Chemical Corporation
A subsidiary of Occidental Petroleum Corporation

14555 Dallas Parkway, Suite 400
Dallas, Texas 75254
800-752-5151

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling, storage, disposal and other factors that may involve other or additional legal, environmental, safety or performance considerations, and Occidental Chemical Corporation assumes no liability whatsoever for the use of or reliance upon this information. While our technical personnel will be happy to respond to questions, safe handling and use of the product remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State, local or foreign laws.