



# OxyVinyls<sup>®</sup> 185



## General Description

Type: Polyvinyl Chloride Homopolymer  
Polymerization Process: Suspension  
Appearance: White, free flowing powder

## Features and Uses:

Injection molding, Pipe fittings  
Calendering  
Flooring  
Extrusion, clear film and sheet  
Rigid foam profiles

Resin Properties	Specification Range	Test Method
Inherent Viscosity (dl/g)	0.660 – 0.700	OxyVinyls 1386
Relative Viscosity	1.78 – 1.85	Correlation
K Value	55 – 57	Correlation
Volatiles (%)	0.40 Max.	OxyVinyls 1242
Malvern Particle Size		
% Retained on 40 mesh	0.5 Max.	OxyVinyls 1505
% Retained on 60 mesh	3.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	25.0 Max.	
% Retained on Pan	6.0 Max.	
Contamination (#/100gm)	30 Max.	OxyVinyls 1504
Residual Monomer (ppm)	3.2 Max.	OxyVinyls 1005
Apparent Bulk Density (g/cc)	0.525 – 0.605	OxyVinyls 1501
Flow Time (s)	14 Max.	OxyVinyls 1501

## Oxy Vinyls, LP

5005 LBJ Freeway  
Dallas, Texas 75244  
877-699-8465

August 2017  
Pasadena, TX

**Important:** The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.