



SALES SPECIFICATION

Anhydrous Calcium Chloride 94-97% Mini-Pellets (Bulk)

| <u>Property</u> | <u>Minimum</u> | <u>Maximum</u> |
|--|----------------|----------------|
| Calcium Chloride (wt. %) | 94 | |
| Total Alkali Chlorides as NaCl (wt. %) | | 6.0 |
| Total Magnesium as MgCl ₂ (wt. %) | | 0.5 |
| Calcium Hydroxide (wt. %) | | 0.2 |
| Passing No. 4 (4.76 mm) sieve (wt. %) | 100 | |
| Passing No. 8 (2.38 mm) sieve (wt. %) | 80 | |
| Passing No. 20 (0.84 mm) sieve (wt. %) | | 10 |
| Passing No. 30 (0.6 mm) sieve (wt. %) | | 1 |
| Bulk Density, Tapped (lb/ft ³) | 52 | 58 |

Material description: white, odorless pellets

Total Alkali Chlorides as NaCl (wt %), Total Magnesium as MgCl₂ (wt %) and Calcium Hydroxide (wt %) limits are shown on an "Active Ingredient" basis.

Meets ASTM D98 and AASHTO M144 requirements.

SS-MPB Sep 2018