

OxyVinyls® 355



General Description

Type: Polyvinyl Chloride Homopolymer

Polymerization Process: Suspension

Appearance: White, free flowing powder

Features and Uses:

High Molecular Weight Excellent Plasticizer Absorption and Dryup

Useful for Calendered and Extruded Materials requiring High Strength, Abrasion Resistance, Fatigue Resistance, Grain Retention, Impact, Cut-through, and Other Physical Properties

Resin Properties	Specification Range	Test Method
Inherent Viscosity (dl/g)	1.570 – 1.630	OxyVinyls 1386
Relative Viscosity	3.48 – 3.65	Correlation
K Value	87 – 89	Correlation
Volatiles (%)	0.30 Max.	OxyVinyls 1242
Malvern Particle Size		
% Retained on 40 mesh	0.2 Max.	OxyVinyls 1505
% Retained on 60 mesh	4.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	12.0 Max.	
% Retained on Pan	2.0 Max.	
Contamination (#/100gm)	15 Max.	OxyVinyls 1504
Residual Monomer (ppm)	2.0 Max.	OxyVinyls 1005
Porosity (cc/g)	0.370 - 0.510	OxyVinyls 1094
Apparent Bulk Density (g/cc)	0.390 - 0.480	OxyVinyls 1501

Oxy Vinyls, LP

5005 LBJ Freeway Dallas, Texas 75244 877-699-8465 **Important:** The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.